

AD-A220 802

REF ID: A220 802 COPY

4

OFFICE OF NAVAL RESEARCH  
CONTRACT NO. N000 14 85 K 0177  
R & T Code 431a003-4

Technical Report No. 15

PREPARATION AND PROPERTIES OF IRON DOPED II-VI CHALCOGENIDES

BY

J. DiCarlo, M. Albert, K. Dwight and A. Wold

Prepared for Publication in  
JOURNAL OF SOLID STATE CHEMISTRY

March 29, 1990

Brown University  
Department of Chemistry  
Providence, Rhode Island 02912

DTIC  
ELECTE  
APR 17, 1990  
S B D

Reproduction in whole or in part is permitted for any  
purpose of the United States Government

This document has been approved for public release and sale;  
its distribution is unlimited

90 04 16 099

## REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION <b>UNCLASSIFIED</b>			1b. RESTRICTIVE MARKINGS	
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION/AVAILABILITY OF REPORT <b>APPROVED FOR PUBLIC RELEASE DISTRIBUTION UNLIMITED</b>	
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE				
4. PERFORMING ORGANIZATION REPORT NUMBER(S) <b>#15</b>			5. MONITORING ORGANIZATION REPORT NUMBER(S) <b>N00014-85-K-0177</b>	
6a. NAME OF PERFORMING ORGANIZATION <b>BROWN UNIVERSITY AARON WOLD</b>		6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION <b>OFFICE OF NAVAL RESEARCH R. SCHWARTZ</b>	
6c. ADDRESS (City, State, and ZIP Code) <b>DEPARTMENT OF CHEMISTRY BROWN UNIVERSITY PROVIDENCE, RI 02912</b>		7b. ADDRESS (City, State, and ZIP Code) <b>CODE 373 NAVAL WEAPONS CENTER CHINA LAKE, CA 93555</b>		
8a. NAME OF FUNDING/SPONSORING ORGANIZATION		8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER	
8c. ADDRESS (City, State, and ZIP Code)		10. SOURCE OF FUNDING NUMBERS		
		PROGRAM ELEMENT NO	PROJECT NO	TASK NO
		WORK UNIT NO		
11. TITLE (Include Security Classification) <b>THE PREPARATION AND PROPERTIES OF IRON DOPED II-VI CHALCOGENIDES</b>				
12. PERSONAL AUTHOR(S) <b>J. DiCarlo, M. Albert, K. Dwight and A. Wold</b>				
13a. TYPE OF REPORT <b>Technical</b>		13b. TIME COVERED FROM _____ TO _____		14. DATE OF REPORT (Year, Month, Day) <b>March 29, 1990</b>
15. PAGE COUNT <b>15</b>				
16. SUPPLEMENTARY NOTATION <b>PREPARED FOR PUBLICATION IN JOURNAL OF SOLID STATE CHEMISTRY</b>				
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB-GROUP		
19. ABSTRACT (Continue on reverse if necessary and identify by block number)				
<p>Semi-magnetic semiconductors are a class of doped II-VI compounds which are of interest in the study of magnetic interactions. Samples of iron-doped <u>ZnS</u>, <u>ZnSe</u> and <u>CdS</u> were prepared by the direct combination of the elements. Magnetic measurements indicate that the antiferromagnetic interactions of the iron in the zinc systems were greater than those observed in the cadmium chalcogenides. Single crystals of iron-doped zinc chalcogenides were grown by chemical vapor transport. Their IR transmission was measured and the iron concentration for maximum hardness was determined. (R-1)</p>				
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION	
22a. NAME OF RESPONSIBLE INDIVIDUAL			22b. TELEPHONE (Include Area Code)	22c. OFFICE SYMBOL

THE PREPARATION AND PROPERTIES OF IRON DOPED II-VI CHALCOGENIDES

J. DiCarlo, M. Albert, K. Dwight and A. Wold

Department of Chemistry, Brown University

Providence, Rhode Island 02912

### Abstract

Semi-magnetic semiconductors are a class of doped II-VI compounds which are of interest in the study of magnetic interactions. Samples of iron-doped ZnS, ZnSe, and CdS were prepared by the direct combination of the elements. Magnetic measurements indicate that the antiferromagnetic interactions of the iron in the zinc systems were greater than those observed in the cadmium chalcogenides. Single crystals of iron-doped zinc chalcogenides were grown by chemical vapor transport. Their IR transmission was measured and the iron concentration for maximum hardness was determined.



<b>Accession For</b>	
NTIS GRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

## Introduction

The substitution of magnetic ions into II-VI semiconductors results in a class of materials known as semi-magnetic semiconductors which are of interest to the physics community. The II-VI chalcogenides containing manganese have been extensively studied and their magnetic properties appear to be well understood (1-3). Studies have also been performed where iron is substituted for zinc in the II-VI semiconductors (4-12). The two systems which have received much attention are  $\text{Zn}_{1-x}\text{Fe}_x\text{Se}$  and  $\text{Cd}_{1-x}\text{Fe}_x\text{Se}$  (8-12). There has, however, been little reported work on the dilute magnetic semiconductors  $\text{Zn}_{1-x}\text{Fe}_x\text{S}$  and  $\text{Cd}_{1-x}\text{Fe}_x\text{S}$ . Barton and Toulmin (13) have reported that the solubility limit of iron in the system  $\text{Zn}_{1-x}\text{Fe}_x\text{S}$  was 58 mole percent iron. Papalardo and Dietz (14) studied the spectra of iron-doped CdS; however, no magnetic measurements were performed in their study.

ZnS and ZnSe have been used as IR windows because of their wide transmission range in the infrared. However, both ZnS and ZnSe are soft, which limits their suitability for some applications. It was noted (15,16) that in the systems  $\text{Zn}_{1-x}\text{Ni}_x\text{S}$  and  $(\text{GaP})_x(\text{ZnSe})_{1-x}$  the infrared spectra were not changed appreciably from those of pure ZnS and ZnSe, but the hardness was enhanced significantly. Ni(II) ( $3d^8$ ) prefers octahedral coordination and it has been shown that it is difficult to introduce a significant quantity of Ni(II) into the structure (15). Since it has been reported that up to 58 mole percent iron can be substituted for zinc at  $890^\circ\text{C}$ , it should be possible to modify the properties of II-VI compounds using iron as a component. This paper concerns itself with the preparation and characterization of the systems  $\text{Zn}_{1-x}\text{Fe}_x\text{S}(\text{Se})$  for both powder and single crystal samples and  $\text{Cd}_{1-x}\text{Fe}_x\text{S}$  for powder samples. The study includes problems associated with attempts to

prepare single phase materials, as well as the magnetic behavior of Fe(II) in a tetrahedral site, IR transmission, hardness and stability in oxygen.

## Experimental

### Preparation

Polycrystalline samples were prepared by using stoichiometric amounts of zinc metal (Gallard and Schlesinger 99.9995%), cadmium metal (Cominco EM 8001, 99.999%), selenium (UMC 23333 99.999%), iron (Leico 46987) pre-reduced in Ar/H<sub>2</sub> (85/15), sulfur (Gallard and Schlesinger 99.999%) sublimed prior to use and iodine (sublimed, Deepwater Chemical Co., Std. ACS reagent 99.9%). The appropriate weights of the reactants to give a total weight of 3 grams of product were sealed in evacuated 12 mm silica tubes, and heated in the following manner: 500°C for 48 hrs, 600°C for 48 hrs. The tubes were then transferred to a two-zone furnace and the charge end was maintained at 800°C and the other end at 450°C for 48 hrs in order to complete the reaction between the metal and sulfur or selenium without exploding the sample tubes. The samples were then heated at 700°C for 48 hrs, 800°C for 48 hrs, and 900°C for 96 hrs. The samples were intimately mixed after each heat treatment.

### Crystal Growth

Stoichiometric amounts of zinc, iron and sulfur or selenium were placed in a silica tube (14 mm O.D. x 12 mm I.D.) which had been previously heated to near the melting point to minimize any nucleation sites. The tube was evacuated to 10<sup>-5</sup> torr and freshly sublimed iodine was introduced as the transport agent at a concentration of 5 mg/cc. The tube was sealed off and enclosed in a tightly wound Kanthal coil (to even out temperature gradients) and the whole assembly was placed in a three-zone furnace (17). The crystal growth temperature procedure consisted of setting the furnace to back

41

transport mode for one day, equilibrating the furnace to the maximum temperature for three hours, and finally, cooling the growth zone at 1°C/hr to the growth temperature. Optimum crystal growth for  $\text{Zn}_{1-x}\text{Fe}_x\text{S}$  and  $\text{Zn}_{1-x}\text{Fe}_x\text{Se}$  occurred when the charge zone was maintained at 965°C and the growth zone at 870°C. The transport process was carried out for 5 days and the typical crystal size was 3 x 3 x 1 mm. The actual composition of the single crystal was determined from the magnetic measurements.

#### Characterization of Products

X-ray powder diffraction patterns of the samples were obtained using a Philips diffractometer and monochromated high intensity  $\text{CuK}\alpha_1$  radiation ( $\lambda = 1.5405\text{\AA}$ ). For qualitative phase identification, diffraction patterns were taken over the range  $12^\circ < 2\theta < 72^\circ$  with a scan rate of  $1^\circ 2\theta/\text{min}$ , while cell parameters were determined from scans taken with a scan rate of  $0.25^\circ 2\theta/\text{min}$ . Precise lattice parameters were obtained from the diffraction peaks using a least-squares refinement program which corrects for the systematic errors of the diffractometer.

Optical measurements on polished single crystals were performed at room temperature on a Perkin-Elmer 580 single beam scanning infrared spectrophotometer. The measurements were performed in the transmission mode over the range  $2.5\ \mu\text{m} - 25\ \mu\text{m}$ . Transmission through the sample was normalized to the signal obtained in the absence of the sample.

The microhardness measurements (Knoop indenter) were made on crystals using a Kentron microhardness tester. The results were obtained using a diamond indenter with 25 gram loads for  $\text{Zn}_{1-x}\text{Fe}_x\text{S}$  and 10 grams for  $\text{Zn}_{1-x}\text{Fe}_x\text{Se}$ .

The stability of these compounds toward oxidation was determined by heating them in a flowing oxygen stream (60 sccm) and monitoring the change in weight during the heating period. The decomposition temperature was determined as the temperature where the weight of the sample began to change.

Magnetic susceptibilities were measured from liquid nitrogen temperature (77 K) to 500 K using a Faraday balance at a field strength of 10.4 kOe. Honda-Owens (field dependency) plots were also made and all magnetic susceptibility data were corrected for diamagnetism.

### Results and Discussion

Polycrystalline samples of  $\text{Zn}_{1-x}\text{Fe}_x\text{S}$ ,  $\text{Zn}_{1-x}\text{Fe}_x\text{Se}$  and  $\text{Cd}_{1-x}\text{Fe}_x\text{S}$  were prepared directly from the elements. Samples of  $\text{Cd}_{1-x}\text{Fe}_x\text{Se}$  have been prepared and studied by Smith (12). X-ray diffraction patterns indicated that the zinc iron sulfide and zinc iron selenide products were single phase and crystallized with the cubic zinc-blende structure. The cadmium iron sulfide and cadmium iron selenide also were single phase and crystallized with the hexagonal wurtzite structure.

For the system  $\text{Zn}_{1-x}\text{Fe}_x\text{S}$ , compositions were chosen where  $x = 0.03, 0.10, 0.15, 0.25, \text{ and } 0.30$ . It was found for this system that the limit of solubility of iron in ZnS was 30 atomic % for the above method of preparation. It was also found that the 30% sample appeared to be single phase by x-ray diffraction; however, the magnetic susceptibility showed field dependent behavior (Fig. 1), indicating the presence of an impurity with a spontaneous moment; this magnetic impurity decreased with continued heating. Although the sample where  $x = 0.30$  appeared single phase by x-ray diffraction after only 4 days of reaction time at  $900^\circ\text{C}$ , it was found that 16 additional days of



heating at 900°C were necessary in order to obtain a field independent material (Fig. 1). This result demonstrated the importance of magnetic susceptibility measurements in determining completeness of reaction in the system  $\text{Zn}_{1-x}\text{Fe}_x\text{S}$ . The maximum solubility limit of iron in zinc sulfide has previously been determined by Barton and Toulmin (13) to be 58 mole percent iron at 890°C. The samples in their studies took an average of 6 months to show single phase material as indicated by x-ray diffraction analysis. Furthermore, it was found that control of the sulfur pressure was necessary for the preparation of samples containing high iron content.

For the system  $\text{Zn}_{1-x}\text{Fe}_x\text{Se}$ , compositions were chosen where  $x = 0.03, 0.10, 0.15, 0.20$ , and  $0.25$ . All samples appeared to be single phase as indicated by x-ray diffraction analysis; however, the  $x = 0.25$  sample showed field dependent behavior. Unlike the  $\text{Zn}_{.70}\text{Fe}_{.30}\text{S}$  sample, continued heating of the selenide did not improve its field dependent behavior. Therefore, the solubility limit of iron in zinc selenide is between 20 and 25 atomic percent iron. This limit of solubility of iron in zinc selenide is in agreement with the work of Twardowski, who reported that a maximum of 22 mole percent iron could be substituted for zinc in  $\text{ZnSe}$  boules grown from the melt (8).

For the system  $\text{Cd}_{1-x}\text{Fe}_x\text{S}$ , compositions were chosen where  $x = 0.03, 0.10, 0.15, 0.20$  and  $0.25$ . All samples appeared to be single phase as indicated by x-ray diffraction analysis. The  $x = 0.25$  sample showed field dependent behavior, but became field independent after 12 additional days of heating at 850°C. Thus, 25 atomic % appears to be the solubility limit of Fe in  $\text{CdS}$ .

For all the samples listed in Table 1, the magnetic moment per  $\text{Fe(II)}$  obtained from magnetic susceptibility data remains  $5.4(1) \mu_B$  regardless of

iron content. The Weiss constants are negative, indicating antiferromagnetic Fe-Fe interactions, and become more negative with increasing iron substitution for zinc or cadmium. The Weiss constants of the  $\text{Zn}_{1-x}\text{Fe}_x\text{S}$  and  $\text{Zn}_{1-x}\text{Fe}_x\text{Se}$  systems are essentially the same. The Weiss constants of the  $\text{Cd}_{1-x}\text{Fe}_x\text{S}$  and  $\text{Cd}_{1-x}\text{Fe}_x\text{Se}$  systems are also equivalent, but are markedly smaller than those obtained for the zinc systems, which indicates that weaker antiferromagnetic interactions occur in the cadmium systems. This difference in the strength in antiferromagnetic interactions has been also observed when cobalt is substituted for zinc and cadmium in these systems. Niu et al. (18) indicated that the observed differences in the strength of the antiferromagnetic interactions were related to the increase in the Co-Co effective distances in the cadmium systems.

Single crystals of  $\text{Zn}_{1-x}\text{Fe}_x\text{S}$  and  $\text{Zn}_{1-x}\text{Fe}_x\text{Se}$  were grown by chemical vapor transport using iodine as the transport agent. All of the products crystallized with the cubic zinc-blende structure and showed field independent behavior. The iron concentration of crystals was obtained by comparing their room temperature susceptibilities with the susceptibilities obtained from polycrystalline samples of known iron content (Fig. 2). Several crystals of each system were grown and their IR properties as well as their hardness and thermal stability were determined (Table 2). It can be seen that the addition of iron below 16 mole percent did not affect transmission at the long wavelength end, but a cut off at the high energy end was observed.

Hardness measurements were made on these samples and showed that initially the addition of iron caused an increase in hardness. Larger substitutions of iron did not further affect the hardness. Thermal stability measurements showed that there was very little affect on the thermal stability as the amount of iron substituted for zinc was increased in these systems.

### Acknowledgments

This research received partial support from the National Science Foundation Contract No. 890 1270, from the Office of Naval Research, and from the Exxon Education Foundation and the Eastman Kodak Company.

### References

1. N. B. Brandt and V. V. Moshchalkov, *Adv. Phys.*, 33, 193 (1984).
2. J. K. Furdyna, *J. Appl. Phys.*, 53, 7637 (1982).
3. J. K. Furdyna and N. Smarath, *J. Appl. Phys.*, 61, 3526 (1987).
4. A. K. Komarov, S. M. Ryabchenko and O. V. Terletski, *Phys. Stat. Solidi B*, 102, 603 (1980).
5. W. Law and M. Weger, *Phys Rev.*, 118 (5), 1130 (1960).
6. A. Petrou, X. Liu, G. Waytena, J. Warnock and W. Giriat, *Solid State Commun.*, 61, 767 (1987).
7. D. Heiman, A. Petrou, E. D. Isaacs, S. H. Bloom, Y Shapira and W. Giriat, *Phys. Rev. Lett.*, 60, 1876 (1988).
8. A. Twardowski, P. Gold, W. J. M. de Jonge and M. Demeaniuk, *Solid State Commun.*, 64, 63 (1987).
9. H. Swagten, A. Twardowski and W. J. M. de Jonge, *Phys. Rev B* 39 (4), 2568 (1989).
10. A. Twardowski, A. Lewicki, M. Arciszewska, W. J. M. de Jonge, H. Swagten, and M. Demianiuk, *Phys Rev. B*, 38 (15), 10-749 (1988).
11. A. Twardowski, M. Von Ortenberg and M. Demeaniuk, *J. of Cryst. Growth*, 72, 401 (1985).

12. K. Smith, J. Marsella, K. Dwight and A. Wold, *Mats. Res. Bull.*, 23, 1423 (1988).
13. P. Barton and P. Toulmin, *Economic Geology*, 61, (5), 815 (1966).
14. R. Pappalardo and R. Dietz, *Phys Rev.*, 123 (4) 1188 (1961).
15. P. W. R. Kershaw, K. Dwight and A. Wold, *Mats. Res. Bull.*, 24, 49 (1989).
16. H-S. Shen, G-Q. Yao, X-C. He, K. Dwight and A. Wold, *Mats Res. Bull.*, 23, 153 (1988).
17. R. Kershaw, M. Vlasse and A. Wold, *Inorganic Chemistry*, 6, 1599 (1967).
18. C-M. Niu, R. Kershaw, K. Dwight and A. Wold. "The Preparation and Properties of Cobalt-Doped II-VI Chalcogenides. Submitted to J. Sol. State Chem.

Table 1

## Summary of Properties of Iron-Substituted II-VI Chalcogenides

Compound	Cell Constant (Å)		Moment (Bohr (magnetons)	Weiss Constant ( K )	Cell Volume
	a	c			
ZnS	5.409(2)	-----	---	---	---
Zn <sub>.97</sub> Fe <sub>.03</sub> S	5.410(2)	-----	5.3	- 55(5)	---
Zn <sub>.90</sub> Fe <sub>.10</sub> S	5.415(2)	-----	5.5	-184(5)	---
Zn <sub>.85</sub> Fe <sub>.15</sub> S	5.417(2)	-----	5.4	-224(5)	---
Zn <sub>.75</sub> Fe <sub>.25</sub> S	5.418(2)	-----	5.4	-365(5)	---
Zn <sub>.70</sub> Fe <sub>.30</sub> S	5.420(2)	-----	5.5	-564(5)	---
ZnSe	5.667(2)	-----	---	---	---
Zn <sub>.97</sub> Fe <sub>.03</sub> Se	5.668(2)	-----	5.2	- 49(5)	---
Zn <sub>.90</sub> Fe <sub>.10</sub> Se	5.675(2)	-----	5.5	-166(5)	---
Zn <sub>.85</sub> Fe <sub>.15</sub> Se	5.676(2)	-----	5.3	-199(5)	---
Zn <sub>.80</sub> Fe <sub>.20</sub> Se	5.677(2)	-----	5.4	-284(5)	---
CdS	4.136(2)	6.715(2)	---	---	---
Cd <sub>.97</sub> Fe <sub>.03</sub> S	4.126(2)	6.700(2)	5.3	- 23(5)	---
Cd <sub>.90</sub> Fe <sub>.10</sub> S	4.105(2)	6.667(2)	5.3	- 85(5)	---
Cd <sub>.85</sub> Fe <sub>.15</sub> S	4.094(2)	6.651(2)	5.4	-135(5)	---
Cd <sub>.80</sub> Fe <sub>.20</sub> S	4.079(2)	6.634(2)	5.3	-149(5)	---
Cd <sub>.75</sub> Fe <sub>.25</sub> S	4.073(2)	6.621(2)	5.4	-224(5)	---
*CdSe			---	---	112.3
*Cd <sub>.98</sub> Fe <sub>.02</sub> Se			5.3	- 17	112.0
*Cd <sub>.95</sub> Fe <sub>.05</sub> Se			5.6	- 41	111.6

\* Obtained from Smith et al. (12): cell volume is expressed instead of cell constants.

Table 2

## Properties of Single Crystals of Iron-Substituted ZnS and ZnSe


%Fe	Hardness (kg/mm <sup>2</sup> )	IR Transmission (microns)	Thermal Stability (Centigrade)
<u>ZnS</u>			
0.00	158	2.5 - 14	520
0.03	176	6.0 - 14	530
0.10	184	6.0 - 14	540
0.16	180	6.0 - 12	540
<u>ZnSe</u>			
0.00	104	2.5 - 20	420
0.03	149	6.0 - 20	380
0.10	136	6.5 - 20	360
0.16	136	6.5 - 18	370

### Figure Captions

Fig. 1. Variation of effective magnetic susceptibility with inverse magnetic field as a function of time-at-temperature.

Fig. 2. Variation of magnetic susceptibility with composition of standard polycrystalline samples of ZnS, ZnSe, and CdS

$\text{Zn}_{.70}\text{Fe}_{.30}\text{S}$





# Polycrystalline Standards

